

## REPOORT ON CHEMICAL ANALYSIS OF ADMIXTURE

Page No. 1/1

<b>Client</b>	TOUGH BUILD BUILDING PREFECTION	<b>Report No.</b>	ARM23025305
<b>Contractor</b>	NO SPECIFIC CONTRACTOR	<b>Date Reported</b>	30/11/24
<b>Consultant</b>	NO SPECIFIC CONTRACTOR	<b>Sample No.</b>	ASM23007464
<b>Project No.</b>	N.P.	<b>Request No.</b>	ASM23007464
<b>Project Name</b>	Internal Testing	<b>Client Ref.</b>	N.P.
<b>Sample Description</b>	TOUGHPLAST-150	<b>Sampled By</b>	Client's Rep.
<b>Source</b>	TOUGH BUILD BUILDING PREFECTION	<b>Sampling Date</b>	N.P.
<b>Location Sample</b>	N.P.	<b>Sampling Cert.</b>	N.P.
<b>Lot No.</b>	N.P.	<b>Sampling Method</b>	N.P.
<b>Lot Size.</b>	N.P.	<b>Sample Size</b>	N.P.
<b>Sample Preparation</b>	N.P.	<b>Sample Brt. In By</b>	Client's Rep.
<b>Test Method</b>	ASTM C494	<b>Date Received</b>	10/12/24
<b>Test Method Var.</b>	NONE	<b>Date Tested</b>	12/12/24
<b>Tested Location</b>	ACES Dubai Lab	<b>Tested By</b>	Abbas
<b>Remarks</b>	-		

TYPE OF TEST	RESULT
pH@25°C	4.7
Solid Content(%)	37.7
Specific Gravity	1.07
Appearance	Light Brown Liquid



  
**Sindhu Anil Kumar**  
 Head of Environment Technical Section

**Notes:** 1. The test results in this report relate only to the test sample as received and tested by the laboratory. 2. Unless otherwise stated in Remarks, all samples were received in acceptable condition. 3. This report shall not be reproduced except in full, without written approval of ACES.

**Disclaimer:** Unless otherwise stated, Client and project details as well as sampling and sample identification information included in this report are provided by the Client. ACES shall not be liable for any incorrect results arising from unclear, erroneous, incomplete, misleading or false information provided by the Client.

**Form:** RT-2770-150

- END OF REPORT -



ص.ب : ١٠٨٢٣، دبي - ا.ع.م. ، هاتف : +٩٧١-٤-٨٨٥١٤١١ ، فاكس : +٩٧١-٤-٨٨٥١٤١٠  
 P.O. Box : 60823, Dubai - U A E, Tel. : +971-4-8856466, Fax : +971-4-8856460  
 E-mail : acesdubai@aces-int.com Website: www.aces-int.com

Abu Dhabi : Tel. +971 2 5502774  
 Al Ain : Tel. +971 3 7211533  
 Sharjah : Tel. +971 6 5619798